



CODE **EASYMID A BKIG**

DESCRIPTION **PA66 BLACK**

REV 01 ISSUED 18/03/2021

PROPERTIES	UNITS	VALUE - DAM	METHOD
PHISICAL			
DENSITY	g/cm ³	1,13	ISO 1183
MOISTURE ABSORPTION 24h at 23° in H2O*	%	2,90	INTERNAL
MOISTURE ABSORPTION saturation*	%	-	INTERNAL
MOULDING SHRINKAGE: ALONG FLOW*	%	1,4-1,9	INTERNAL
MOULDING SHRINKAGE: ACROSS FLOW*	%	1,4-1,9	INTERNAL
MECHANICAL			
TENSILE STRENGHT*	MPa	60	ISO 527-2
TENSILE MODULUS*	MPa	2500	ISO 527-2
FLEXURAL STRENGHT*	MPa	70	ISO 178
FLEXURAL MODULUS*	MPa	2000	ISO 178
IZOD IMPACT STRENGHT NOTCHED 23°C	KJ/m ²	6	ISO 180/A
THERMIC			
HDT/A (1,8 Mpa)	°C	70	ISO 75-2
FLAMMABILITY			
FLAME RATING (1,6 mm – 3,2 mm)*	CLASS	HB	UL 94
GLOW WIRE FLAMMABILITY INDEX (1 mm)*	°C	-	IEC 60695-2-12
PROCESSING			
PREDRYING TEMPERATURE	°C	80	90
PREDRYING TIME	h	3	4
RECOMMENDED MELT TEMPERATURE	°C	260	310

Compound di poliammide (PA) riciclato realizzato con una percentuale dal 70% al 98% derivante da scarti post-industriali (PIR) della linea commerciale EASYMID.

Recycled polyamide (PA) compound obtained from post-industrial waste in the quantity between 70% and 98%, named EASYMID.



This document is propriety of Powerpol s.r.l. and can't be used without our autorization. Values in this data sheet are only indicatives, they are not product specifications. We cannot forecast every conditions where our informations and our products will be used, then we can't guarantee applicability fitness for a specific use. For this reason we decline any responsibility for damage to customers and others.

* : values only indicative, they aren't product specifications and aren't checked by our quality system.

POWERPOL S.r.L.

Legal Office: Via Moncalieri 19/b, 10029 Villastellone (TO) - ITALY

Operative & Administration Office: Via Moncalieri 19/b, 10029 Villastellone (TO) - ITALY

VAT IT11252150013 | Cap. Soc. 10.000 euro i.v. | www.powerpol.it