



CODE **EASYMID B GF35 BKIG**

DESCRIPTION **PA6 35%GF BLACK**

REV 01 ISSUED 18/03/2021

PROPERTIES	UNITS	VALUE - DAM	METHOD
<b>PHISICAL</b>			
DENSITY	g/cm <sup>3</sup>	1,38	ISO 1183
MOISTURE ABSORPTION 24h at 23° in H2O*	%	2,4-2,7	INTERNAL
MOISTURE ABSORPTION saturation*	%	7,4-7,7	INTERNAL
MOULDING SHRINKAGE: ALONG FLOW*	%	0,3-0,5	INTERNAL
MOULDING SHRINKAGE: ACROSS FLOW*	%	0,7-0,9	INTERNAL
<b>MECHANICAL</b>			
TENSILE STRENGHT*	MPa	135	ISO 527-2
TENSILE MODULUS*	MPa	7500	ISO 527-2
FLEXURAL STRENGHT*	MPa	150	ISO 178
FLEXURAL MODULUS*	MPa	7000	ISO 178
IZOD IMPACT STRENGHT NOTCHED 23°C	KJ/m <sup>2</sup>	10	ISO 180/A
<b>THERMIC</b>			
HDT/A (1,8 Mpa)	°C	200	ISO 75-2
<b>FLAMMABILITY</b>			
FLAME RATING (1,6 mm – 3,2 mm)*	CLASS	HB	UL 94
GLOW WIRE FLAMMABILITY INDEX (1 mm)*	°C	-	IEC 60695-2-12
<b>PROCESSING</b>			
PREDRYING TEMPERATURE	°C	80	90
PREDRYING TIME	h	3	4
RECOMMENDED MELT TEMPERATURE	°C	250	280

Compound di poliammide (PA) riciclato realizzato con una percentuale dal 70% al 98% derivante da scarti post-industriali (PIR) della linea commerciale EASYMID.

*Recycled polyamide (PA) compound obtained from post-industrial waste in the quantity between 70% and 98%, named EASYMID.*



This document is propriety of Powerpol s.r.l. and can't be used without our autorization. Values in this data sheet are only indicatives, they are not product specifications. We cannot forecast every conditions where our informations and our products will be used, then we can't guarantee applicability fitness for a specific use. For this reason we decline any responsibility for damage to customers and others.

\* : values only indicative, they aren't product specifications and aren't checked by our quality system.