


THETA COMPOUNDS

Technical Data Sheet



CODE **THETALENE H2 MT40E03 BK1000**

DESCRIPTION *PP HOMO 40% TALC BLACK*

REV 01

ISSUED 18/03/2021

PROPERTIES	UNITS	VALUE	METHOD
PHISICAL			
SPECIFIC GRAVITY	g/cm ³	1.25	ISO 1183
MELT FLOW INDEX (230°C - 2,16 Kg)	g/10'	5-10	ISO 1133
MOISTURE ABSORPTION 24h at 23° in H2O*	%	-	INTERNAL
MOISTURE ABSORPTION saturation*	%	-	INTERNAL
MOULDING SHRINKAGE: ALONG FLOW*	%	0,5-1,0	INTERNAL
MOULDING SHRINKAGE: ACROSS FLOW*	%	0,5-1,0	INTERNAL
MECHANICAL			
TENSILE STRENGHT*	MPa	30	ISO 527-2
TENSILE MODULUS*	MPa	-	ISO 527-2
FLEXURAL STRENGHT*	MPa	45	ISO 178
FLEXURAL MODULUS*	MPa	3600	ISO 178
IZOD IMPACT STRENGHT NOTCHED 23°C	KJ/m ²	3	ISO 180/A
THERMIC			
VICAT/B (50N; 120° C/h)	°C	95	ISO 306
HDT/A (1,8 Mpa)	°C	75	ISO 75-2
FLAMMABILITY			
FLAME RATING (1,6 mm – 3,2 mm)*	CLASS	HB	UL 94
GLOW WIRE FLAMMABILITY INDEX (1 mm)*	°C	-	IEC 60695-2-12
PROCESSING			
PREDRYING TEMPERATURE	°C	40	60
PREDRYING TEMPERATURE TIME	h	2	3
RECOMMENDED MELT TEMPERATURE	°C	210	260

Compound di polipropilene (PP) di prima scelta realizzata utilizzando unicamente materie prime vergini.

First choice polypropylene (PP) compound made using only virgin raw materials.

This document is propriety of Powerpol s.r.l. and can't be used without our autorization. Values in this data sheet are only indicatives, they are not product specifications. We cannot forecast every conditions where our informations and our products will be used, then we can't guarantee applicability fitness for a specific use. For this reason we decline any responsibility for damage to customers and others.

* : values only indicative, they aren't product specifications and aren't checked by our quality system.

POWERPOL S.r.L.

Legal Office: Via Moncalieri 19/b, 10029 Villastellone (TO) - ITALY

Operative & Admistration Office: Via Moncalieri 19/b, 10029 Villastellone (TO) - ITALY

VAT IT11252150013 | Cap. Soc. 10.000 euro i.v. | www.powerpol.it

