


THETA COMPOUNDS

Technical Data Sheet



CODE **THETAMID B GF30SP BK1000**

DESCRIPTION **PA6 30%GF PS BLACK**

REV 01

ISSUED 18/03/2021

PROPERTIES	UNITS	VALUE - DAM		METHOD
PHISICAL				
DENSITY	g/cm ³	1,35		ISO 1183
MOISTURE ABSORPTION 24h at 23° in H2O*	%	2,4-2,7		INTERNAL
MOISTURE ABSORPTION saturation*	%	7,4-7,7		INTERNAL
MOULDING SHRINKAGE: ALONG FLOW*	%	0,3 - 0,5		INTERNAL
MOULDING SHRINKAGE: ACROSS FLOW*	%	0,7 - 0,9		INTERNAL
MECHANICAL				
TENSILE STRENGHT*	MPa	170		ISO 527-2
TENSILE MODULUS*	MPa	9300		ISO 527-2
FLEXURAL STRENGHT*	MPa	200		ISO 178
FLEXURAL MODULUS*	MPa	9000		ISO 178
IZOD IMPACT STRENGHT NOTCHED 23°C	KJ/m ²	12		ISO 180/A
THERMIC				
HDT/A (1,8 Mpa)	°C	210		ISO 75-2
FLAMMABILITY				
FLAME RATING (1,6 mm – 3,2 mm)	CLASS	HB		UL 94
GLOW WIRE FLAMMABILITY INDEX (1 mm)	°C	-		IEC 60695-2-12
PROCESSING				
PREDRYING TEMPERATURE	°C	80	90	
PREDRYING TEMPERATURE TIME	h	3	4	
RECOMMENDED MELT TEMPERATURE	°C	250	280	

Compound di poliammide (PA) di prima scelta realizzata utilizzando unicamente materie prime vergini.

First choice polyamide (PA) compound made using only virgin raw materials.

This document is propriety of Powerpol s.r.l. and can't be used without our autorization. Values in this data sheet are only indicatives, they are not product specifications. We cannot forecast every conditions where our informations and our products will be used, then we can't guarantee applicability fitness for a specific use. For this reason we decline any responsibility for damage to customers and others.

* : values only indicative, they aren't product specifications and aren't checked by our quality system.

POWERPOL S.r.L.

Legal Office: Via Moncalieri 19/b, 10029 Villastellone (TO) - ITALY

Operative & Administration Office: Via Moncalieri 19/b, 10029 Villastellone (TO) - ITALY

VAT IT11252150013 | Cap. Soc. 10.000 euro i.v. | www.powerpol.it

